



**ADULT OUTERWEAR**

Number: BURL-013  
 Creation Date: 1/24/2018  
 Revision Date: 5/15/2018  
 Created by: Legal Dept.

TEST DESCRIPTION	REGULATION/TEST METHOD	REQUIREMENTS									
<b>MANDATORY</b>											
<b>Sew-in Label Verification</b> - Fiber Content - Country of Origin - Care Instructions - Registration Number (RN) or Wool products Registration Number (WPL)	FTC Textile Fiber ID Act 16 CFR 303 16 CFR 300 19 CFR 134	Must Comply									
Law Labeling (For filling clothing)	Various States Regulation	1- States require manufacturer of quilted clothing to get registration number in one of the state and maintain registration in relevant states. 2- For filling material made of wool, feathers, down, shoddy, and hair, the sterilization permit number (PER. NO.) shall be listed on the textile label. 3- Contents of Down, Goose Down, or Duck Down shall also state's the minimum percentage.									
Fiber Content	AATCC 20/20A	Single fiber $\pm$ 0.0% Blends $\pm$ 3.0%									
Wearing Apparel Flammability	16 CFR Parts 1610	Shall meet Class 1 requirements									
Dimensional Stability to Laundering -	AATCC 150	<table border="0"> <tr> <td></td> <td>% Length</td> <td>% Width</td> </tr> <tr> <td>Basic - Natural</td> <td>5 X</td> <td>5</td> </tr> <tr> <td>Basic - Synthetic</td> <td>3 X</td> <td>3</td> </tr> </table>		% Length	% Width	Basic - Natural	5 X	5	Basic - Synthetic	3 X	3
	% Length	% Width									
Basic - Natural	5 X	5									
Basic - Synthetic	3 X	3									
Dimensional Stability to Dry Cleaning	AATCC 158	<table border="0"> <tr> <td>% Length</td> <td>% Width</td> </tr> <tr> <td>3 X</td> <td>3</td> </tr> </table>	% Length	% Width	3 X	3					
% Length	% Width										
3 X	3										
Colorfastness to Laundering/ Dry Cleaning	AATCC 107	Shade Change: Grade 4 minimum Staining: Grade 3 minimum Self -Staining: Grade 5/ No Self Staining									
General Appearance After Laundering 3 Home Launderings	Visual Evaluation	- No open raveling, open seams, or tufting damage. - No obvious defects/observations affecting the end product performance/appearance. - Color Change: Grade 4 - Self staining: Grade 4 - List all observations									
Colorfastness to Chlorine Bleach	AATCC TS-001	Grade 4									
Colorfastness to Non-Chlorine Bleach	AATCC TS-001	Grade 4									
Colorfastness to Crocking	AATCC 8/116	Dry: Grade 4 minimum Wet: Grade 3 minimum									
Rain Test (If Claimed to be Waterproof)	AATCC 35	Maximum 1g of water penetration @2 ft/2 minute.									
Spray Test (If Claimed to be Water Resistant)	AATCC 22	Original – 90 Washed, after 3 HL-70									
<b>STATES REGULATIONS</b>											
Total heavy metals in packaging	Toxics in Packaging Clearinghouse (TPCH)	Packaging shall not contain the sum of mercury, cadmium, lead and chromium (VI) in concentration above 0.01% by weight.									



Plastic Bag Warnings	Various state laws	Plastic bags with a thickness of less than 1 mil (0.001 inch) having an opened end larger than 5 inches in diameter shall contain the following warning statement or equivalent: <b>WARNING: To avoid danger of suffocation, keep this plastic bag away from babies and children. Do not use this bag in cribs, beds, carriages or playpens. This bag is not a toy.</b>
California Prop 65	Warning label or applicable testing	In lieu of warning label, product should meet all applicable Prop 65 requirements.
<b>OPTION (QUALITY &amp; PERFORMANCE)</b>		
Thread Count	ASTM D3775	Thread Count
Weight	ASTM D3776	As Specified (+/- 5%)
Yarn Size	ASTM D1059	As Specified (+/- 10%)
Formaldehyde (Spot Test)	AATCC 94	No Trace If trace is found - proceed with full testing
Formaldehyde	JIS 1041 LAW 112	< 75 ppm
pH of Water Extract	pH of Water Extract	Whites: 5.5 - 6.5, Others: 6 - 8
Colorfastness to Light	AATCC 16 Option 3 40 hours	Step 4
Torque (Knits only)	AATCC 179 Method 2, Option 3	5.0% Max
Tensile Strength (Wovens)	ASTM D5034	40 x 30 lbs. (warp x weft)
Tear Strength (Wovens)	ASTM D1424	3.0 x 2.5 lbs. (warp x weft)
Bursting Strength (Knits)	ASTM D 3786	50 PSI
Seam Strength	ASTM D 1683	All Seams: 30 lbs. Minimum Bartacks and reinforcements: 20 lbs. Min
Pilling Resistance (Woven) Martindale Pilling Method 100 Movements	ASTM D4970	Grade 3.5 minimum
Pilling Resistance (Knit) Random Tumble Pilling Resistance	ASTM D3512	Grade 3.5 Minimum after 30 minutes
Attachment Strength Snaps Buttons, Shanks, Rivets, etc. Hand-Sewn Beads, Sequins, etc.	ASTM D7142 Opt. 2 16 CFR 1500.50-53 16 CFR 1500.50-53	15 lb. / 10 sec. 15 lb. / 10 sec. 5 lb. / 10 sec
Zipper Operability (open/close)	ASTM D2062	3 lb. maximum