

**HANDBAGS**

Number: BURL-085  
 Creation Date: 12/19/2017  
 Revision Date: 5/15/2018  
 Created by: Legal Dept.

TEST DESCRIPTION	REGULATION/TEST METHOD	REQUIREMENTS
<b>MANDATORY</b>		
Label Verification	F.P. & L. Act (16 CFR 500) OR NIST Uniform Laws and Regulations Handbook 130	Manufacturer, packer, or distributor's name & address (city, state & zip)
		Product Identification
		Net quantity of contents shall be expressed in terms of weight or mass, measure, numerical count, or combination so as to give accurate information to facilitate consumer comparison (U.S. and metric units).
		Fiber content
Fiber Content (textile)	AATCC 20/20A	Single fiber $\pm$ 0.0% Blends $\pm$ 3.0%
Labeling of genuine leather and imitation leather  (If applicable)	16 CFR 24	1- imitation or simulated leather should be disclosed 2- Embossed or processed leather 3- Backing material 4- Ground, pulverized, shredded, reconstituted, or bonded leather
Country of Origin Marking	19 CFR 134.11	Shall indicate country of origin legibly, permanently, and incomparable size and close proximity to any mention of country other than country in which the article was manufactured or produced. Must be visible at point of purchase.
California Prop 65	Warning label or applicable testing	In lieu of warning label, product should meet all applicable Prop 65 requirements.
Total heavy metals in packaging	Toxics in Packaging Clearinghouse (TPCH)	Packaging shall not contain the sum of mercury, cadmium, lead and chromium (VI) in concentration above 0.01% by weight.
Plastic Bag Warnings	Various state laws	Plastic bags with a thickness of less than 1 mil (0.001 inch) having an opened end larger than 5 inches in diameter shall contain the following warning statement or equivalent: <b>WARNING: To avoid danger of suffocation, keep this plastic bag away from babies and children. Do not use this bag in cribs, beds, carriages or playpens. This bag is not a toy.</b>
<b>NON-MANDATORY (QUALITY &amp; PERFORMANCE)</b>		
Formaldehyde (Spot Test)	AATCC 94	No Trace If trace is found - proceed with full testing
Formaldehyde	JIS 1041 LAW 112	<75 ppm
Colorfastness to Crocking	AATCC 8/116	Dry: Grade 4 minimum Wet: Grade 3 minimum
Attachment Strength	ASTM 1683	Shoulder Strap: $\geq$ 75 lbs. Handle Strap: $\geq$ 40 lbs. Pockets: $\geq$ 11 lbs.



Hardware Operability (Claps, Closure Fasteners, Zipper, Buckles, D-Rings, Mics Hardware)	Actual Use	Open/Close Or Attach/Re-Attach 100 times Operability and appearance should not change
Tensile Strength (Wovens)	ASTM D5034	40 x 25 lbs. (warp x weft)
Tear Strength (Wovens)	ASTM D1424	3.0 x 2.5 lbs. (warp x weft)
Seam Strength(Wovens)	ASTM D 1683	Across Each Seam: 45 lbs. Minimum Bartacks and reinforcements: 20 lbs. Min