



**TABLE LINEN: Table Cloth, Placemat & Napkins
(fabric, vinyl or plastics)**

Number: BURL-008
 Creation Date: 12/19/2017
 Revision Date: 5/15/2018
 Created by: Legal Dept.

TEST DESCRIPTION	REGULATION/TEST METHOD	REQUIREMENTS
Mandatory		
Fiber analysis	AATCC 20/20A	Single Fiber: No tolerance Blended Fiber: +/- 3%
Label Verification	F.P. & L. Act (16 CFR 500) OR NIST Uniform Laws and Regulations Handbook 130 FTC regulation	Manufacturer, packer, or distributor's name & address (city, state & zip) Or RN #
		Product Identification
		Net quantity of contents shall be expressed in terms of weight or mass, measure, numerical count, or combination so as to give accurate information to facilitate consumer comparison (U.S. and metric units).
		Fiber content (textile only)
Fiber analysis (textile only)	AATCC 20/20A	Single Fiber: No tolerance Blended Fiber: +/- 3%
Country of Origin Marking	19 CFR 134.11	Shall indicate country of origin legibly, permanently, and incomparable size and close proximity to any mention of country other than country in which the article was manufactured or produced. Must be visible at point of purchase.
California Prop 65	Warning label or applicable testing	In lieu of warning label, product should meet all applicable Prop 65 requirements.
Non-Mandatory (Quality & Performance) for Table Cloth and Napkins made of fabric only		
Colorfastness to Water (Except white and cream color)	AATCC 107	Color Change: Print and pigment: 3.5 min., others 4 min. Color Staining: Print and pigment: 3.5 min., others 4 min. Self-staining: 4.5 min.
Colorfastness to Light	AATCC 16.3 (20AFU)	Color Change: Medium to dark colors: 4 min. Pastels, bright & neon colors: 3.5 min.
Colorfastness to Crocking (Except white and cream color)	AATCC 8 / AATCC 116	Dry: 4 min. Wet: 2.5 min.
Colorfastness to Laundering	AATCC 61	Color Change: Print and pigment: 3.5 min., others 4 min. Color Staining: Print and pigment: 3.5 min., others 4 min. Self-staining: 4.5 min.