



Number: BURL-010

Creation Date: 4/24/2018

Revision Date: 5/15/2018

Created by: Legal Dept.

WINDOW CURTAINS & VALENCES (Adult)

TEST DESCRIPTION	REGULATION/TEST METHOD	REQUIREMENTS									
MANDATORY											
Label Verification	F.P. & L. Act (16 CFR 500) OR NIST Uniform Laws and Regulations Handbook 130 FTC requirement for fiber content	Manufacturer, packer, or distributor's name & address (city, state & zip)									
		Product Identification									
		Net quantity of contents shall be expressed in terms of weight or mass, measure, numerical count, or combination so as to give accurate information to facilitate consumer comparison (U.S. and metric units).									
		Fiber content									
Country of Origin Marking	19 CFR 134.11	Shall indicate country of origin legibly, permanently, and incomparable size and close proximity to any mention of country other than country in which the article was manufactured or produced. Must be visible at point of purchase.									
Fiber analysis	AATCC 20/20A	Single Fiber: No tolerance Blended Fiber: +/- 3%									
California Prop 65	Warning label or applicable testing	In lieu of warning label, product should meet all applicable Prop 65 requirements.									
Light Blocking Effect of Curtain Material – Room Darkening Claim	AATCC 148	98% or more blockage.									
OPTIONAL (PERFORMANCE & QUALITY) MANDATORY											
Colorfastness to Crocking	AATCC 8 / 116	Dry: Grade 4 min. Wet: Grade 3 min.									
Colorfastness to Light	AATCC 16.3 Option 3	Grade 4.0 min @40 AFU									
Dimensional Stability to Laundering - Woven	AATCC 150	<table border="0"> <tr> <td></td> <td>% Length</td> <td>% Width</td> </tr> <tr> <td>Basic - Natural</td> <td>5</td> <td>X 5</td> </tr> <tr> <td>Basic - Synthetic</td> <td>3</td> <td>X 3</td> </tr> </table>		% Length	% Width	Basic - Natural	5	X 5	Basic - Synthetic	3	X 3
	% Length	% Width									
Basic - Natural	5	X 5									
Basic - Synthetic	3	X 3									
General Appearance After Laundering 3 Home Launderings	Visual Evaluation	<ul style="list-style-type: none"> - No open raveling, open seams, or tufting damage. - No obvious defects/observations affecting the end product performance/appearance. - Shade Change: Grade 4 - Self staining: Grade 5 - List all observations 									
Attachment Strength Snaps Buttons, Shanks, Rivets, etc. Hand-Sewn Beads, Sequins, etc.	ASTM D7142 Opt. 2 16 CFR 1500.50-53 16 CFR 1500.50-53	15 lb. / 10 sec. 15 lb. / 10 sec. 5 lb. / 10 sec									
Resistance to Corrosion (For metal component)	ASTM B117	Metal component shall withstand 24 hours in 5% salt spray (fog) with no major corrosion									